

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20023344

07-20

REQUIRED TESTS	RESULT	COMMENTS
PHYSICAL PROPERTIES		
Breathability(Differential Pressure)	P	
P: Pass F: Fail R: Refer to retailer technologist. Test results were performed and evaluated according to EN 14683:2019+AC:2019 Annex -C/Table- 1 limit values		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified.If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20023344

07-20

TEST RESULTS

BREATHABILITY (Differential Pressure)

Test Metodu: EN 14683:2019+AC :2019 (TS EN 14683+AC:2019) EK-C (*)

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

Test area is 25 mm in diameter , 5 different sample was taken

Adjusted airflow is 8 l/min.The differential pressure is read directly using a differential pressure manometer .

SAMPLE	DIFFERENTIAL PRESSURE RESULT	REQUIREMENT
1	27.9 Pa/cm ²	< 40 Pa/cm ²
2	23.8 Pa/cm ²	
3	28.1 Pa/cm ²	
4	27.8 Pa/cm ²	
5	21.7 Pa/cm ²	
Average Result	25.8 Pa/cm ²	