

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

20038512-
ing

10-20

TEST RESULTS

BREATHABILITY (Differential Pressure)

Test Metodu: EN 14683:2019+AC :2019 (TS EN 14683+AC:2019) EK-C

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

Test area is 25 mm in diameter , 5 different sample was taken

Adjusted airflow is 8 l/min. The differential pressure is read directly using a differential pressure manometer .

ORIGINAL		
SAMPLE	DIFFERENTIAL PRESSURE RESULT	REQUIREMENT
1	22.0 Pa/cm ²	< 60 Pa/cm ²
2	21.1 Pa/cm ²	
3	21.2 Pa/cm ²	
4	20.4 Pa/cm ²	
5	20.7 Pa/cm ²	
Average Result	21.0 Pa/cm ²	

Gen.f136-2/03

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

20038512-
ing

10-20

TEST RESULTS

BREATHABILITY (Differential Pressure)

Test Metodu: EN 14683:2019+AC :2019 (TS EN 14683+AC:2019) EK-C

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

Test area is 25 mm in diameter , 5 different sample was taken

Adjusted airflow is 8 l/min. The differential pressure is read directly using a differential pressure manometer .

AFTER WASH		
SAMPLE	DIFFERENTIAL PRESSURE RESULT	REQUIREMENT
1	20.8 Pa/cm ²	< 60 Pa/cm ²
2	20.1 Pa/cm ²	
3	21.4 Pa/cm ²	
4	16.2 Pa/cm ²	
5	20.2 Pa/cm ²	
Average Result	19.7 Pa/cm ²	